

IN THE SPECIFICATION

Please replace the paragraph beginning at page 3, line 4 as follows:

Rhenium (calculated as the metal) is present in an amount of from 0.1 to 20% by weight, preferably from 0.5 to 13% by weight, more preferably from 2 to 7% by weight, based on the total mass of the catalyst composed of catalytic active composition and support material. The catalyst according to the invention comprises ~~palladium~~ platinum (calculated as the metal) in an amount of from 0.05 to 10% by weight, preferably from 0.1 to 8% by weight, more preferably from 0.3 to 4% by weight, based on the total mass of the catalyst composed of catalytic active composition and support material.

Please insert pages 8 through 13, which are attached to the Appendix at the end of this document, between pages 7 and 14 of the specification as filed.